

# CERTIFICATE OF CONFORMANCE

## Everlast™ Polymeric Cladding

Everlast Polymeric Cladding panels are manufactured to the following specifications.

### PHYSICAL DATA

Panel Thickness: 0.22" ( $\pm 0.005$ "  
 Panel Projection:  $\frac{7}{16}$ "  
 Width:  $8\frac{1}{2}$ "  $\pm \frac{1}{16}$ " and  $6\frac{3}{8}$ "  $\pm \frac{1}{16}$ "  
 Exposure:  $6\frac{7}{8}$ " &  $4\frac{1}{2}$ "  
 Length: 12'  
 Weight:  $6\frac{7}{8}$ " plank = 7.8#,  $4\frac{1}{2}$ " plank = 6.4#  
 Packaging: 8 planks/bundle  
 Color: Uniformity is spectrophotometrically controlled.  
 Texture: Embossed with a rough cut cedar finish  
 Gloss: Uniform low gloss maintained with a 75° gloss meter

### PRODUCT TEST DATA

Heat Shrinkage:	0.1% at 160°F
Static Windload Test Pressure:	93 psf. (>250mph)
Squareness:	<1/16" of square
Length:	Within - 1/4" of specification
Warp/Camber:	<1/16"
Coefficient of Linear Expansion (in/in/°F):	$8.38 \times 10^{-6}$
Weathering and Flexural:	104.4% Strength Retention
Freeze Thaw and Flexural:	94.1% Strength Retention
Water Absorption per ASTM D-570:	<2.0% Long Term (3 weeks)

### FIRE RESISTANCE

#### ASTM E84:

Flame Spread Index: 75  
 Smoke Developed Index: >450

#### ASTM D635:

Classified CC1  
 Rate of burn: No Self Sustained Burn

#### ASTM D-1929:

Self Ignition/Flash Ignition Temperature: 430°C/400°C

### RELEVANT CODES AND REGULATIONS COMPLIANCE

Code Compliance Research Report #0201



0201

### COLORS

- Antique Ivory
- Cabernet Red
- Canvas
- Chestnut
- Flagstone
- Harbor Blue
- Heritage Cream
- Misty Taupe
- Polar White
- Sand Dune
- Seaside Gray
- Slate
- Spanish Moss
- Willow

*All colors feature ColorHold® capping resins, a UV- Stable acrylic polymer for exceptional color retention.*

